

Duplocoll 2501

Art. No.

Double coated film tape.

Product Construction

	Name	Color	Thickness – mm/mil
Liner	Paper	White	Approx. 0.05 / 2.0
Adhesive-covered side	Formulated rubber	Clear	Approx. 0.03 / 1.0
Carrier	PET	Clear	Approx. 0.01 / 0.5
Adhesive-open side	Formulated rubber	Clear	Approx. 0.03 / 1.0
		Tape Thickness:	Approx. 0.07 / 2.5
		Total Thickness:	Approx. 0.12 / 4.5

Product Advantages

- Light tack, permanent adhesive on both sides of a thin film carrier.
- Designed for use on "bubble bags" and very thin films where a permanent, but not a tamper evident closure is needed.
- The adhesive may be off-set to the left or right.
- Can be provided with a paper or polypropylene release liner and is available in pancake rolls or cross-wound spools.

Main Application Fields

- Permanent poly bag closure systems.

Product Features

Applicability on:


Initial adhesion	●●●	Foam	●●○
Final adhesion	●●●	Rubber	●●○
Dimensional stability	●●●	Fabric	●●○
Adhesion on smooth surfaces	●●●	Glass/Ceramic	●●●
Adhesion on rough surfaces	●●○	Wood	●●●
Aging resistance	●●○	High energy	●●●
Weathering resistance	●●○	Low energy	●●○
Chemical resistance	●○○	Metal	●●●
Plasticizer resistance	●○○	Paper/Cardboard	●●○
●●● very suitable	●●○ suitable	●○○ somewhat suitable	○○○ not suitable

Duplocoll 2501

Double coated film tape.

Technical Data

Shear Strength	On SS, PSTC 107A, 72 ± 2°F	> 36 hrs
Peel Strength	On SS, PSTC 101A, 72 ± 2°F	78 Oz/in
Temperature Range		-20 to +170°F



Application

Recommended application temperature	65 to 95°F
Application guidelines	www.lohmanncorp.com

Storage

Adhesive tapes should be stored at room temperature and normal humidity (50 – 70%). The storage stability is one year.

Product Presentation

Converted Product	Standard Rolls	Spools
Width:		
Length:		
Max. log width:	Specific dimensions available upon request	

Physical characteristics contained in our data sheets for trial, new, or modified products represent typical or average values. They have no statistical relevance and must not be used for technical specification purposes.

All application related statements, information, and recommendations, herein, are given to the best of our knowledge and practical experience. The buyer is responsible for determining the suitability of the tape specific tape for its intended use in connection with the user's method of application. Please consult our Technical Application Department for specific advice.

Our general terms of sale apply, particularly with regard to warranty and liability.

Issued: December 7, 2009, LAR

Lohmann Technologies
3000 Earhart Ct., Suite 155
Hebron, KY 41048
Tel. 859-334-4900
Fax 859-334-4903
www.lohmanncorp.com

